

## SECTION 066116 – SOLID SURFACING FABRICATIONS

## PART 1 - GENERAL

## 1.01 SUMMARY

- A. Section Includes: Provide solid surfacing fabrications including but not limited to following:
  - 1. Wall cap at Gathering Stair.
- B. Related Sections: Following description of work is included for reference only and shall not be presumed complete:
  - 1. Provision of elastomeric joint sealants: Section 079200, Joint Sealants.

## 1.02 REFERENCES

- A. Abbreviations and Acronyms:
  - 1. LEED®: Leadership in Energy and Environmental Design; [www.cagbc.org](http://www.cagbc.org).
  - 2. VOC: Volatile Organic Compound.
- B. Definitions:
  - 1. Solid Surface: Non-porous, homogeneous material maintaining the same composition throughout the part with a composition of acrylic polymer, aluminum trihydrate filler and pigment.
- C. Reference Standards:
  - 1. ASTM C920-14a - Standard Specification for Elastomeric Joint Sealants
  - 2. ASTM D638-10 - Standard Test Method for Tensile Properties of Plastics
  - 3. ASTM D785-08 - Standard Test Method for Rockwell Hardness of Plastics and Electrical Insulating Materials
  - 4. ASTM D790-10- Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
  - 5. ASTM D5420-10 - Standard Test Method for Impact Resistance of Flat, Rigid Plastic Specimen by Means of a Striker Impacted by a Falling Weight (Gardner Impact)
  - 6. ASTM E84-14 - Standard Test Method for Surface Burning Characteristics of Building Materials
  - 7. ASTM E228-11 - Standard Test Method for Linear Thermal Expansion of Solid Materials with a Push-Rod Dilatometer
  - 8. ASTM G21-13 - Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi
  - 9. ASTM G22-76(96) - Standard Practice for Determining Resistance of Plastics to Bacteria
  - 10. NFPA 255-06 - Standard Method of Test of Surface Burning Characteristics of Building Materials
  - 11. UL 723 - Standard for Test for Surface Burning Characteristics of Building Materials

## 1.03 ADMINISTRATIVE REQUIREMENTS

- A. Preinstallation Meetings: Arrange preinstallation meeting 1 week prior to commencing work with all parties associated with trade as designated in Contract Documents or as requested by Architect. Presided over by Contractor, include Architect who may attend, Subcontractor performing work of this trade, Owner's representative, testing company's representative and consultants of applicable discipline. Review Contract Documents for work included under this trade and determine complete understanding of requirements and responsibilities relative to work included, storage and handling of materials, materials to be used, installation of materials, sequence and quality control, Project staffing, restrictions on areas of work and other matters affecting construction, to permit compliance with intent of work of this Section.

#### 1.04 SUBMITTALS

- A. Product Data: Indicate Product description including solid surface sheets, sinks, bowls and illustrating full range of standard colors, fabrication information and compliance with specified performance requirements. Submit Product data with resistance to list of chemicals.
- B. Shop Drawings: Submit Shop Drawings for work of this Section in accordance with Section 01 30 00. Indicate plans, sections, dimensions, component sizes, edge details, thermosetting requirements, fabrication details, attachment provisions, sizes of furring, blocking, including concealed blocking and coordination requirements with adjacent work. Show locations and sizes of cutouts and holes for plumbing fixtures, faucets, soap dispensers, waste receptacles and other items installed in solid surface.
- C. Coordination Drawings: Submit coordination drawings indicating plumbing and miscellaneous steel work indicating locations of wall rated or non-rated, blocking requirements, locations and recessed wall items and similar items.
- D. Samples: Submit samples in accordance with Section 01 30 00. Submit minimum 6" x 6" samples. Cut sample and seam together for representation of inconspicuous seam. Indicate full range of color and pattern variation. Approved samples will be retained as standards for work.
- E. Test and Evaluation Reports: Submit flammability test reports.

#### 1.05 CLOSEOUT SUBMITTALS

- A. Operational and Maintenance Data:
  - 1. Submit manufacturer's care and maintenance data, including repair and cleaning instructions. Include in Project closeout documents.
  - 2. Provide a commercial care and maintenance kit and video. Review maintenance procedures and warranty details with Owner upon completion.

#### 1.06 QUALITY ASSURANCE

- A. Qualifications:
  - 1. Installers: Provide work of this Section executed by competent installers with minimum 5 years experience in the application of Products, systems and assemblies specified and with approval and training of the Product manufacturers.
- B. Mock-Ups:

1. Prior to final approval of Shop Drawings, erect 1 full size mock-up of each component at Project site demonstrating quality of materials and execution for Architect review.
2. Should mock-up not be approved, rework or remake until approval is secured. Remove rejected units from Project site.
3. Approved mock-up will be used as standard for acceptance of subsequent work.
4. Approved mock-ups may remain as part of finished work.

#### 1.07 DELIVERY, STORAGE AND HANDLING

- A. Delivery and Acceptance Requirements: Deliver no components to Project site until areas are ready for installation.
- B. Storage and Handling Requirements:
  1. Store components indoors prior to installation.
  2. Handle materials to prevent damage to finished surfaces.

#### 1.08 WARRANTY

- A. Manufacturer Warranty: Provide manufacturer's standard warranty for material only for period of 10 years against defects and/or deficiencies in accordance with General Conditions of the Contract. Promptly correct any defects or deficiencies which become apparent within warranty period, to satisfaction of Architect and at no expense to Owner.

### PART 2 - PRODUCTS

#### 2.01 MANUFACTURERS

- A. Manufacturer List: Products of following manufacturers are acceptable subject to conformance to requirements of Drawings, Schedules and Specifications:
  1. Corian® by DuPont; [www.corian.com](http://www.corian.com)
  2. Samsung Chemical USA; [www.staron.com](http://www.staron.com)
  3. Wilsonart Contract; [www.wilsonartcontract.com](http://www.wilsonartcontract.com)
- B. Substitution Limitations: This Specification is based on Corian® Products. Comparable Products from manufacturers listed herein will be accepted provided they meet requirements of this Specification.

#### 2.02 MATERIALS

- A. Description:
- B. Performance/Design Criteria:

Property	Requirement (min or max)	Test Procedure
1. Solid Surface Based Products:		
a. Tensile Strength	6000 psi min	ASTM D638

b.	Tensile Modulus	$1.5 \times 10^6$ psi min	ASTM D638
c.	Tensile Elongation	0.4% min.	ASTM D638
d.	Flexural Strength	10000 psi min	ASTM D790
e.	Flexural Modulus	$1.2 \times 10^6$ psi min	ASTM D790
f.	Hardness	>85-Rockwell "M" scale min.	ASTM D785
g.	Thermal Expansion	$2.2 \times 10^{-5}$ in./in./°F	ASTM E228
h.	Fungi and Bacteria	Does not support microbial growth	ASTM G21 & G22
i.	Microbial Resistance	Highly resistant to mold growth	UL 2824
j.	Ball Impact	No fracture - 1/2 lb. Ball: NEMA LD 3, 6 mm slab - 36" drop 12 mm slab - 144" drop	Method 3.8
k.	Weatherability	$\Delta E^*94 < 5$ in 1,000 hrs	ASTM G155
l.	Flammability		ASTM E84, NFPA 255 & UL 723

**All Colors**

	<b>6 mm</b>	<b>12 mm</b>	
m.	Flame Spread	<25	
n.	Smoke Developed	<25	
o.	Class	A	NFPA 101®, Life Safety Code

C. Solid Surface Material:

D. Non-porous, homogeneous material maintaining the same composition throughout the part with a composition of acrylic polymer, aluminum trihydrate filler and pigment; not coated, laminated or of composite construction; meeting following criteria:

E. Flammability: Class 1 and A when tested to UL 723.

F. Adhesive for Bonding to Other Products: One component silicone to ASTM C920.

G. Sealant: A standard mildew-resistant, FDA/UL® and NSF/ANSI 51 compliant in Food Zone area, recognized silicone color matched sealant or clear silicone sealants.

H. Heat Reflecting Tape: Manufacturer's standard aluminum foil tape, with required thickness, for use with cutouts near heat sources.

I. Insulating Nomex® Fabric: Manufacturer's standard for use with conductive tape in insulating solid surface material from adjacent heat source.

## 2.03 COMPONENTS

- A. Wall cap: 1/2" thick solid surfacing material, adhesively joined with inconspicuous seams, edge details as indicated on Drawings. Color selected later by Architect from manufacturer's full color range.
- B. Fabrication:
  - 1. Fabricate components in shop to greatest extent practical to sizes and shapes indicated, in accordance with approved Shop Drawings and solid polymer manufacturer requirements. Form joints between components using manufacturer's standard joint adhesive without conspicuous joints.
  - 2. Where indicated, thermoform corners and edges or other objects to shapes and sizes indicated on Drawings, prior to seaming and joining. Cut components larger than finished dimensions and sand edges to remove nicks and scratches. Heat entire component uniformly prior to forming.
  - 3. Ensure no blistering, whitening and cracking of components during forming.
  - 4. Fabricate joints between components using manufacturer's standard joint adhesive. Ensure joints are inconspicuous in appearance and without voids. Attach 50 mm (2") wide reinforcing strip of solid polymer material under each joint. Reinforcing strip of solid polymer material is not required when using DuPont™ Joint Adhesive 2.0.
  - 5. Rout and finish component edges to a smooth, uniform finish. Rout cutouts, then sand edges smooth. Repair or reject defective or inaccurate work.
  - 6. Finish: Ensure surfaces have uniform finish:
    - a. Matte, with a 60° gloss rating of 5 - 20.
  - 7. Fabrication Tolerances:
    - a. Variation in Component Size: +/-1/8".
    - b. Location of Openings: +/-1/8" from indicated location.

### PART 3 - EXECUTION

#### 3.01 EXAMINATION

- A. Verification of Conditions:
  - 1. Examine substrates and conditions, with fabricator present for compliance with requirements for installation tolerances and other conditions affecting performance of work. Proceed with installation only after unsatisfactory conditions have been corrected.
  - 2. Verify actual site dimensions and location of adjacent materials prior to commencing work.
  - 3. Examine cabinets upon which counter tops are to be installed. Verify cabinets are level to within 1/8" in 10' - 0".
  - 4. Notify Architect in writing of any conditions which would be detrimental to installation.
- B. Evaluation and Assessment: Commencement of work implies acceptance of previously completed work.

#### 3.02 INSTALLATION

- A. Install components plumb, level, rigid, scribed to adjacent finishes in accordance with reviewed Shop Drawings and Product installation details.
- B. Fabricate field joints using manufacturer's recommended adhesive, with joints being inconspicuous in finished work. Exposed joints/seams are not permitted. Keep components and hands clean when making joints. Reinforce field joints as specified herein. Cut and finish component edges with clean, sharp returns.
- C. Route radii and contours to template. Anchor securely to base component or other supports. Align adjacent components and form seams to comply with manufacturer's written recommendations using adhesive in color to match work. Carefully dress joints smooth, remove surface scratches and clean entire surface.
- D. Install sills with no more than 1/8" sag, bow or other variation from a straight line.
- E. Seal between wall and components with joint sealant as specified herein and in Section 079200, as applicable.
- F. Keep components and hands clean during installation. Remove adhesives, sealants and other stains. Ensure components are clean on date of Substantial Completion of the Work.

### 3.03 REPAIR

- A. Repair minor imperfections and cracked seams and replace areas of severely damaged surfaces in accordance with manufacturer's "Technical Bulletins".

### 3.04 SITE QUALITY CONTROL

- A. Non-Conforming Work: Replace damaged work which cannot be satisfactorily repaired, restored or cleaned, to satisfaction of Architect at no cost to Owner.

### 3.05 CLEANING

- A. Remove excess adhesive and sealant from visible surfaces.
- B. Clean surfaces in accordance with manufacturer's "Care and Maintenance Instructions".

### 3.06 PROTECTION

- A. Provide protective coverings to prevent physical damage or staining following installation for duration of Project.
- B. Protect surfaces from damage until date of Substantial Completion of the Work.

END OF SECTION 066116